

武汉卓凡中天包装材料有限公司

检 验 报 告

规格型号		735*0.045	725*0.045										
订单数量 kg		660	500										
批次		221116B1001	221116B1006										
操作人		雨清/承武/海涛	雨清/承武/海涛										
检验项目	技术要求	检测结果	单项结论	检测结果	单项结论								
润湿张力dyn/cm	≥38	42	OK	42	OK								
宽度偏差mm	±2	2	OK	2	OK								
厚度极限偏差%	±8	5	OK	5	OK								
摩擦系数(G/M2)	静≤0.18	0.188	OK	0.188	OK								
	动≤0.12	0.172	OK	0.172	OK								
拉伸强度 MPA	横向	≥15	23.3	OK	23.2	OK							
	纵向		22.2	OK	22.3	OK							
断裂标称 应变%	横向	≥300	642	OK	638	OK							
	纵向		625	OK	628	OK							
起封温度	≤120	112	OK	112	OK								
感官指标	色泽正常 无异味	色泽正常 无异味	OK	色泽正常 无异味	OK								



制表: 肖华

日期: 2022-11-17