

Customer		Product Model	PE 105			
Batch No.	M230720086	Specification	735mm x 60μm			
Production Date	2023-07-21	Inspection Date	2023-07-21			
Test Standard	GB/T 4456-2008					
Test Items		Unit	Standard	Test Result	Justification	Test method
Tensile strength at break		MPa	≥ 18	30.1	PASS	GB/T1040.3
			≥ 18	28.5	PASS	
Elongation at break		%	≥ 200	500	PASS	GB/T1040.3
			≥ 600	640	PASS	
Coefficients of friction		/	≥ 0.12, ≤ 0.22	0.180	PASS	GB/T10006
			≥ 0.12, ≤ 0.22	0.144	PASS	
Wetting tension		mN/m	≥ 38	38	PASS	GB/T14216
Thickness		%	-8	-5	PASS	GB/T6672
			+8	+5	PASS	
Initial sealing temperature	/	/	/	96	PASS	Pression 0.3MPa Time 1S
Width	/	mm	0-+3	737	PASS	GB/T6673
Appearance	/	/	GB/T4456	PASS	PASS	GB/T4456
Analysis Conclusion		检验合格 Pass the test				
Notes						

Tester

Approver

Printing Date 2023-07-25

